Contents lists available at ScienceDirect



Journal of the European Ceramic Society

journal homepage: www.elsevier.com/locate/jeurceramsoc

Full Length Article

A novel Li₂TiO₃–Li₂CeO₃ ceramic composite with excellent microwave dielectric properties for low-temperature cofired ceramic applications



Journal of the

Weigiong Liu, Ruzhong Zuo*

Institute of Electro Ceramics & Devices, School of Materials Science and Engineering, Hefei University of Technology, Hefei, 230009, PR China

A R T I C L E I N F O

ABSTRACT

Keywords: LTCC Microwave dielectrics properties Co-firing Near-zero $\tau_{\rm f}$

A novel low-temperature sinterable $(1 - x)Li_2TiO_3-xLi_2CeO_3$ (x = 0.08 - 0.16 in molar) microwave dielectric ceramic was successfully prepared by a conventional solid-state reaction method. The X-ray diffraction and scanning electron microscopy analysis revealed the coexistence of two phases with different structures owing to their good chemical stability. Their relative content was easily adjusted to achieve near-zero temperature coefficient of the resonant frequency (τ_f) according to the mixing rule of dielectrics. The low-temperature sintering and desirable microwave dielectric properties can be simultaneously achieved by adding Li₂CeO₃ to the Li₂TiO₃ matrix owing to its low-firing characteristic and opposite-sign τ_f . The composite ceramics with x = 0.14 could be well sintered at 850 °C and exhibited excellent microwave dielectric properties of $\varepsilon_r \sim 21.2$, Qaf \sim 59,039 GHz and $\tau_f \sim -7.4$ ppm/°C. In addition, no chemical reaction was identified between the matrix phase and Ag, suggesting that the Li₂TiO₃-Li₂CeO₃ ceramics might be promising candidates for low-temperature co-fired ceramic applications.

1. Introduction

In the past few years, microwave telecommunication technology has made great achievements. Miniaturization of microwave components is essential for the production of multilayer or chip devices in wireless communications. Low temperature cofired ceramic (LTCC) technology is imperative for the fabrication of modern electronic devices [1]. Dielectric materials for LTCC applications require high relative permittivity ($\epsilon_r > 20$ for miniaturization), low sintering temperature (< 960 °C, the melting temperature of Ag electrode), high quality factor (Qxf > 10,000 GHz), and a near-zero temperature coefficient of resonant frequency ($|\tau_f| \le 10 \text{ ppm/°C}$) [2]. These merits are the key requirements for practical applications. For this purpose, LTCC with suitable dielectric properties has been widely investigated.

Many ceramics have been reported so far because of their good microwave dielectric properties, such as Mg₂SiO₄, Ba(Mg_{1/3}Ta_{2/3})O₃, Mg₄Nb₂O₉, ZnAl₂O₄, etc [3–7]. However, the high sintering temperature (> 1000 °C) and undesirable τ_f values impeded their practical applications. Addition of low-melting-point additives, such as V₂O₅, Bi₂O₃ and B₂O₃, was considered to be the simplest way to lower the sintering temperature [8–10]. The usage of the opposite- τ_f materials was a common way to tailor τ_f values [11,12]. However, these methods usually tended to cause the deterioration in microwave dielectric properties. Hence, searching for new materials with excellent

microwave dielectric properties and low sintering temperatures is still an arduous task for scientific research.

Li₂TiO₃ ceramic with a rock salt structure has attracted extensive attention for its good microwave dielectric properties [13]. Pure Li₂TiO₃ ceramic cannot be well densified at high sintering temperatures (> 1200 °C) because of serious volatilization of lithium. A series of lowmelting-point additives such as ZnO-B2O3, LiF, Li2O-MgO-B2O3 has successfully improved the density of Li2TiO3 ceramic and boosted the Oxf value at the same time. Good microwave dielectric properties $(\varepsilon_r = 20-24, \text{ Qxf} = 15,000-70,000 \text{ GHz} \text{ and } \tau_f = 30 \sim 37 \text{ ppm/°C})$ were obtained at a relatively low sintering temperature (900 °C-950 °C) [14–16]. However, the undesirable τ_f value is another important factor impeding its practical application. It was reported that a few metal oxides (MO, M = Mg, Zn, Ni) can form complete solid solutions with Li2TiO3, and the replacement mechanism can be considered as $3 M^{2+} \leftrightarrow 2Li^+ + Ti^{4+}$ [17,18]. The addition of MO increased the cation ordering degree of Li₂TiO₃ thus resulting in the achievement of high Qxf values. Meanwhile, the change in the tilting angle of oxygen octahedra successfully tailored the τ_f value to near zero. Furthermore, LiF and BCB were added in Li2TiO3-MO (LTM) systems to further decrease the sintering temperature. Good microwave dielectric properties were achieved by Li₂TiO₃-MgO-4 wt% LiF $(\varepsilon_{\rm r} = 15.8,$ Qxf = 64,500 GHz, and $\tau_f = -0.2 \text{ ppm/°C}$ and Li₂TiO₃-NiO-1 wt% BCB ($\epsilon_r = 19$, Qxf = 62,252 GHz, and $\tau_f = -1.65 \text{ ppm/°C}$) at 850 °C

E-mail address: rzzuo@hotmail.com (R. Zuo).

http://dx.doi.org/10.1016/j.jeurceramsoc.2017.07.032

Received 5 June 2017; Received in revised form 25 July 2017; Accepted 28 July 2017 Available online 31 July 2017 [005] 2210 (@ 2017] Usersier Ltd. All sights received

0955-2219/ © 2017 Elsevier Ltd. All rights reserved.

^{*} Corresponding author.







Fig. 2. SEM image on the polished and thermally surface of the x = 0.14 ceramic sintered at 850 °C for 4 h.

Table 1

EDS results for the x = 0.14 sample sintered at 850 °C for 4 h.

fdsdfgs		Elements (atom%)		Total (%)
Points	Ti	Ce	0	
a b	18.2 12.8	0.4 28.0	81.4 59.2	100.0 100.0

for 4 h [18,19].

The addition of new materials with a low sintering temperature, an opposite-sign τ_f value and a good dielectric performance may be the simplest and effective way for simultaneously solving LTCC-oriented problems. Li₂CeO₃ with a CeO₂ structure was reported to have a large τ_f value of -123 ppm/°C, a high Qxf value of $\sim 143,700$ GHz and a relative permittivity of $\epsilon_r ~ {\sim} 15.8$ when sintered at an extremely low temperature (720 °C) [20]. Compared with other $\tau_{\rm f}$ -modifiers and sintering aids, relatively good microwave dielectric properties would make Li₂CeO₃ become a more suitable one. Hence, one can expect that a new diphasic composite material with a near-zero τ_{f} value, a low sintering temperature and a high Qxf value could be obtained by combining Li₂TiO₃ with Li₂CeO₃. The sintering behavior, microstructure, microwave dielectric properties and chemical compatibility with Ag were investigated in detail.

Fig. 1. (a) XRD patterns of (1 - x)Li₂TiO₂-xLi₂CeO₂ ceramics sintered at optimum temperatures, (b) and (c) the locally enlarged diffraction peaks for the Li2TiO3 and Li2CeO3 phases, respectively.

2. Experimental

The $(1 - x)Li_2TiO_3-xLi_2CeO_3$ (x = 0.08 ~ 0.16 in molar) ceramics were prepared by a conventional solid-state reaction method using high-purity starting powders of $\rm Li_2\rm CO_3$ (98.0%), $\rm TiO_2$ (99.0%) and $CeO_2(99.0\%)$. The raw materials were weighed according to the above formula and then ball-milled for 4 h using zirconia balls and alcohol as the medium on a planetary milling machine. The resulting slurries were then rapidly dried and calcined at 800 °C for 6 h in air. The calcined powders were re-milled for 6 h and then mixed together with 5 wt% PVA as a binder. The granulated powders were subsequently pressed into cylinders with dimensions of 10 mm in diameter and 7-8 mm in height. The specimens were first heated at 550 °C in air for 4 h to remove the organic binder, and then sintered at 800 °C ~ 900 °C for 4 h.

The crystal structure of the fired ceramics was identified via an Xray diffractometer (XRD, D/Max2500 V, Rigaku, Japan) using Cu Ka radiation. The bulk densities of the sintered ceramics were measured by the Archimedes method. The microstructure of the pellets was observed using a field-emission scanning electron microscope (FE-SEM; SU8020, JEOL, Tokyo, Japan) equipped with an energy dispersive spectrometer (EDS). Before the SEM observation, the sample was polished and thermally etched at 650 °C for 30 min. Microwave dielectric properties of sintered ceramics were measured using a network analyzer (N5230C, Agilent, Palo Alto, CA) and a temperature chamber (GDW-100, Saiweisi, Changzhou, China). The τ_f values of the samples were measured in the temperature range from 20 °C to 80 °C and calculated by the following equation:

$$f_f = \frac{f_2 - f_1}{f_1(T_2 - T_1)}$$
 (1)

where f_1 and f_2 represent the resonant frequencies at T_1 and T_2 , respectively.

3. Results and discussion

Fig. 1(a) presents the normalized XRD patterns of $(1 - x)Li_2TiO_3$ xLi₂CeO₃ ceramics sintered at optimum temperatures for 4 h. The powder diffraction standard file for Li2CeO3 was considered to be the same with CeO_2 [20]. All the main peaks can be well indexed by Li2TiO3 (JCPDS #33-0831) and CeO2 (JCPDS #81-0792). No other phases can be observed in the whole composition range. The XRD results suggest that no chemical reaction occurred between Li2TiO3 and Li₂CeO₃. The Li₂TiO₃ crystallized in a monoclinic structure with the

τ



Fig. 3. (a) The sample density, (b) ε_r and (c) Qxf values of (1-x)Li₂TiO₃-xLi₂CeO₃ ceramics as a function of sintering temperature.

Fig. 4. (a) The $\ln\epsilon_r$, (b) $(Qxf)^{-1}$ and (c) τ_f values of (1-x)Li_2TiO_3-xLi_2CeO_3 ceramics as a function of the volume fraction of Li_2CeO_3.

Table 2

Comparisons of microwave dielectric ceramics with similar permittivities and low sintering temperatures (${\leq}850$ °C).

composition	S.T. (°C)	ε _r	Qxf (GHz)	$\tau_{\rm f}$ (ppm/°C)	Ref.
Li ₂ TiO ₃ –5 wt% Li ₂ O-MgO- B ₂ O ₃	850	21.4	64100	+26.9	[16]
Li ₂ TiO ₃ -NiO–1 wt % BCB	850	19	62252	-1.65	[18]
$(\text{Li}_{0.5}\text{Ln}_{0.5})\text{MoO}_4$ $(\text{Ln} = \text{Nd},$ $\text{Gd}, \text{Sm}, \text{Ce})$	580–750	19.5–20.6	1990–4570	+209 - + 235	[28]
Na2BiZn2V3O12	600	22.3	19960	+15.5	[29]
PbWO ₄	850	21.6	34500	-22.2	[30]
Pb ₂ MoO ₅	610	19.1	21960	-60	[31]
0.86Li ₂ TiO ₃ - 0.14Li ₂ CeO ₃	850	21.18	59309	-7.4	This work

space group C2/c, and the Li₂CeO₃ crystallized in a cubic structure with the space group Fm-3 m [13,20]. The big difference in their crystal structures might be responsible for the formation of composite ceramics. Moreover, Fig. 1(b) and (c) locally present the strongest diffraction peaks of Li₂TiO₃ and Li₂CeO₃ phases, which were found to slightly shift toward higher angles as x increased from 0.08 to 0.10, and then remain at the same degrees with furthering increasing x. This phenomenon might be related to the ionic diffuse between Li2TiO3 and Li₂CeO₃. The smaller Ti ions could be easier to dissolve into the crystal lattice of Li₂CeO₃, such that the reduced content of Ti⁴⁺ ions would result in the decrement of the unit cell volume of Li2TiO3, corresponding to the diffraction peak shift toward higher angles in Fig. 1(b). At the same time, the replacement of smaller Ti⁴⁺ for Ce⁴⁺ would also result in the decrement of the unit cell volume in the crystal lattice of Li₂CeO₃, corresponding to the diffraction peak shift toward higher angles in Fig. 1(c). The completely different crystal structures between Li₂TiO₃ and Li₂CeO₃ determined the limited solid solubility. As a result, the diffraction peak position did not exhibit obvious changes any more as x was more than 0.08.



Fig. 5. XRD pattern and SEM image of the $x\,=\,0.14$ ceramic sample co-fired with 30 wt% Ag at 850 $^\circ C$ for 4 h.

The SEM image of the x = 0.14 ceramic sintered at 850 °C for 4 h is shown in Fig. 2. It can be noted that two kinds of grains were distributed in the specimen, such as large irregular grains (marked as a), and small roundish grains (marked as b). The EDS analysis was also used to distinguish these two kinds of grains. The EDS results of x = 0.14 sample are listed in Table 1. It can be clearly seen that the large irregular grains mainly contained Ti and O elements, meaning that they belonged to the Li₂TiO₃ phase, and small roundish grains were dominantly composed of Ce and O elements, which should belong to the Li₂CeO₃ phase. Li elements were not detected by EDS because of its light atomic mass. It should be noted that small roundish grains also contained a certain amount of Ti, but large irregular grains contained little Ce, which means that a small amount of Ti^{4+} ions were dissolved in the Li_2CeO_3 crystal lattice, while Ce^{4+} could hardly dissolve in the Li₂TiO₃ crystal lattice. The EDS result kept a good consistency with the above-mentioned XRD result. The basic reason seems to be attributed to the fact that relatively small Ti⁴⁺ ions (0.61 Å) compared with Ce⁴⁺ ions (0.87 Å) would be easily dissolved in the crystal lattice of the other phase [21].

Fig. 3 shows the variation of the sample density, ε_r and Qxf of $(1 - x)Li_2TiO_3$ -x Li_2CeO_3 ceramics as a function of sintering temperature. As shown in Fig. 3(a), the density of each composition firstly increased with increasing sintering temperature, then reached the maximum value at 850 °C, and finally decreased with further increasing sintering temperatures. Fig. 3(b) indicates that the variation of ε_r showed a similar trend to that of the bulk density as a function of sintering temperature. It was reported that the composition, grain size, and the density should primarily contribute to the relative permittivity. Among them, the density of the samples usually affected the relative permittivity markedly [22]. Therefore, the ε_r value increased with increasing sintering temperature up to 850 °C and then decreased thereafter. As shown in Fig. 3(c), the improvement in quality factor of each composition from 800 °C to 850 °C should be attributed to the increase in sample density. The deterioration of Qxf values might be due to the degradation in densification caused by the evaporation of lithium at elevated temperatures [23,24].

Fig. 4 shows $\ln \epsilon_r$, $(Qxf)^{-1}$ and τ_f values of Li₂TiO₃-Li₂CeO₃ ceramics as a function of the volume fraction of Li₂CeO₃. According to the mixing rule, the microwave dielectric properties of a dielectric composite can be described by the following equations [25]:

$$\ln\varepsilon_r = V_1 \ln\varepsilon_{r1} + V_2 \ln\varepsilon_{r2} \tag{2}$$

 $(Qxf)^{-1} = V_1(Qxf)_1^{-1} + V_2(Qxf)_2^{-1}$ (3)

$$\tau_{\rm f} = V_1 \tau_{\rm f1} + V_2 \tau_{\rm f2} \tag{4}$$

where V is the volume fraction of each phase. It can be seen that $ln\epsilon_r$,

 $\left(\text{Qxf}\right)^{-1}$ and τ_{f} in current work have a nearly linear relationship with the volume percentage of the Li_2CeO_3 phase. Fig. 4(a) shows that the $ln\epsilon_r$ values of $(1 - x)Li_2TiO_3-xLi_2CeO_3$ ceramics decreased with increasing the volume fraction of Li₂CeO₃, which could be attributed to a lower ε_r value of Li₂CeO₃ (~15.8) than that of Li₂TiO₃ (~23.3). In addition, the measured $ln\varepsilon_r$ values were found to be close to the calculated $\ln \varepsilon_r$ values, indicating that the mixing rule is applicable. However, the measured Qxf values were found to be lower than calculated values (Fig. 4(b)). This is probably because the quality factor is more easily influenced by other factors such as lattice defects, grain size, and porosity and so on. For τ_f values (Fig. 4(c)), the similar difference between measured and calculated values could be also found in other studies [26,27]. Nevertheless, optimal microwave dielectric properties of $\varepsilon_r \sim 21.2$, Qxf ~ 59,039 GHz, and a near-zero $\tau_f \sim -7.4 \text{ ppm/°C}$ were obtained in 0.86Li₂TiO₃-0.14Li₂CeO₃ ceramics as sintered at 850 °C for 4 h.

Table 2 presents a comparison of microwave dielectric ceramics with similar permittivities and low sintering temperatures (≤ 850 °C). By comparison, PbWO₄, Li₂TiO₃-NiO–1 wt% BCB, 0.45(Na_{0.5}La_{0.5}) MoO₄-0.55(Na_{0.5}Bi_{0.5})MoO₄, and 0.86Li₂TiO₃-0.14Li₂CeO₃ were reported to have relatively small τ_f values. And relatively high Qxf values of 62,252 GHz and 59,309 GHz were obtained in Li₂TiO₃-NiO–1 wt% BCB and 0.86Li₂TiO₃-0.14Li₂CeO₃ respectively. Compared with the former composition, the addition of Li₂CeO₃ can play a crucial role in tailoring undesirable τ_f values and decreasing relatively high sintering temperatures at the same time. A relatively simple processing of the Li₂TiO₃-Li₂CeO₃ composite ceramic might make it be an ideal candidate for practical LTCC applications.

In order to identify the suitability of LTCC applications, the chemical compatibility of the Li₂TiO₃-Li₂CeO₃ composite ceramic with Ag was examined. 30 wt% Ag powder was added into the 0.86Li₂TiO₃-0.14Li₂CeO₃ powder, and the mixture was co-sintered at 850 °C for 4 h. Fig. 5 shows the XRD pattern and SEM image of the co-fired sample at 850 °C. It is noted that all diffraction peaks could be well indexed to Li₂TiO₃, Li₂CeO₃ and Ag, suggesting that no any chemical reaction occurred between the composite ceramic and the Ag particle. This could be further confirmed by the SEM image of the cofired sample, as shown in the inset of Fig. 5. Distinct boundary between the ceramic and the Ag particle could be observed. These results demonstrated an excellent chemical stability between the Li₂TiO₃-Li₂CeO₃ ceramic and the Ag electrode at 850 °C and a large potential of the studied composite for LTCC applications.

4. Conclusions

The $(1 - x)Li_2TiO_3$ -xLi_2CeO₃ composite ceramics were fabricated by a conventional solid-state reaction method. The phase composition, microstructure, sintering behavior and microwave dielectric properties of $(1 - x)Li_2TiO_3$ -xLi_2CeO₃ ceramics were investigated as a function of sintering temperature. The low-temperature sintering, high Qxf value and the temperature stability of resonant frequency can be simultaneously achieved by adding Li_2CeO₃ to the Li_2TiO₃ matrix. The X-ray diffraction and scanning electron microscopy analysis revealed the stable coexistence of two phases with different structures owing to their good chemical stability. The x = 0.14 composite ceramic could be well sintered at 850 °C and exhibited excellent microwave dielectric properties of $\varepsilon_r \sim 21.2$, Qxf $\sim 59,039$ GHz, and $\tau_f \sim -7.4$ ppm/°C. Besides, the composite ceramics exhibited a good chemical compatibility with Ag, showing great potentials for practical applications in various LTCC devices.

Acknowledgement

Financial support from the Anhui Provincial Natural Science Foundation (1508085JGD04) is gratefully acknowledged.

W. Liu, R. Zuo

References

- M.T. Sebastian, H. Jantunen, Low loss dielectric materials for LTCC applications: a review, Int. Mater. Rev. 53 (2008) 57–90.
- [2] M. Valant, D. Suvorov, Chemical compatibility between silver electrodes and lowfiring binary-oxide compounds: conceptual study, J. Am. Ceram. Soc. 83 (2000) 2721–2729.
- [3] T. Sugiyama, T. Tsunooka, K. Kakimoto, H. Ohsato, Microwave dielectric properties of forsterite-based solid solutions, J. Eur. Ceram. Soc. 26 (2006) 2097–2100.
- [4] K.X. Song, X.M. Chen, X.C. Fan, Effects of Mg/Si ratio on microwave dielectric characteristics of forsterite ceramics, J. Am. Ceram. Soc. 90 (2007) 1808–1811.
- [5] K.P. Surendran, M.T. Sebastian, P. Mohanan, R.L. Moreira, A. Dis, Effect of nonstoichiometry on the structure and microwave dielectric properties of Ba (Mg_{0.33}Ta_{0.67})O₃, Chem. Mater. 17 (2005) 142–151.
- [6] H. Ogawa, A. Kan, S. Ishihara, Y. Higashida, Crystal structure of corundum type Mg₄(Nb_{2-x}Ta_x)O₉ microwave dielectric ceramics with low dielectric loss, J. Eur. Ceram. Soc. 23 (2003) 2485–2488.
- [7] W. Lei, W.Z. Lu, D. Liu, J.H. Zhu, Phase evolution and microwave dielectric properties of (1-x)ZnAl₂O₄-xMg₂TiO₄ ceramics, J. Am. Ceram. Soc. 92 (2009) 105–109.
- [8] Q. Zeng, W. Li, J.L. Shi, X.L. Dong, J.K. Guo, Influence of V₂O₅ additions to 5Li₂O-Nb₂O₅-5TiO₂ ceramics on sintering temperature and microwave dielectric properties, J. Am. Ceram. Soc. 90 (2007) 2262–2265.
- [9] E.S. Kim, S.H. Kim, B.I. Lee, Low-temperature sintering and microwave dielectric properties of CaWO₄ ceramics for LTCC applications, J. Eur. Ceram. Soc. 26 (2006) 2101–2104.
- [10] L.X. Pang, D. Zhou, Microwave dielectric properties of low-firing Li₂MO₃ (M = Ti, Zr, Sn) ceramics with B₂O₃-CuO addition, J. Am. Ceram. Soc. 93 (2010) 3614–3617.
- [11] S. Meng, Z. Yue, H. Zhuang, F. Zhao, L. Li, Microwave dielectric properties of Ba₃(VO₄)₂-Mg₂SiO₄ composite ceramics, J. Am. Ceram. Soc. 93 (2010) 359–361.
- [12] H. Zhuang, Z.X. Yue, S.Q. Meng, F. Zhao, L.T. Li, Low-temperature sintering and microwave dielectric properties of Ba₃(VO₄)₂–BaWO₄ ceramic composites, J. Am. Ceram. Soc. 91 (2008) 3738–3741.
- $\label{eq:13} \ensuremath{\text{[13]}} J. Liang, W.Z. Lu, J.M. Wu, J.G. Guan, Microwave dielectric properties of Li_2TiO_3 ceramics sintered at low temperatures, Mater. Sci. Eng. B 176 (2011) 99–102.$
- [14] J. Liang, W.Z. Lu, Microwave dielectric properties of Li₂TiO₃ ceramics doped with ZnO-B₂O₃ frit, J. Am. Ceram. Soc. 92 (2009) 952–954.
- [15] Y.Z. Hao, H. Yang, G.H. Chen, Q.L. Zhang, Microwave dielectric properties of Li₂TiO₃ ceramics doped with LiF for LTCC applications, J. Alloy. Compd. 552 (2013) 173–179.
- [16] G. Chen, M. Hou, Y. Yang, Microwave dielectric properties of low-fired Li₂TiO₃

Journal of the European Ceramic Society 38 (2018) 119-123

ceramics doped with Li₂O-MgO-B₂O₃ frit, Mater. Lett. 89 (2012) 16-18.

- [17] C.L. Huang, Y.W. Tseng, J.Y. Chen, High-Q dielectrics using ZnO-modified Li₂TiO₃ ceramics for microwave applications, J. Eur. Ceram. Soc. 32 (2012) 3287–3295.
- [18] J. Zhang, R. Zuo, Low-temperature fired thermal-stable Li₂TiO₃-NiO microwave dielectric ceramics, J. Mater. Sci.: Mater. Electron. 27 (2016) 7962–7968.
- [19] J.L. Ma, Z.F. Fu, P. Liu, B. Wang, Y. Li, Microwave dielectric properties of low-fired Li₂TiO₃?MgO ceramics for LTCC applications, Mater. Sci. Eng. B 204 (2016) 15–19.
 [20] C.F. Tseng, P.A. Lin, Microwave dielectric properties of novel glass-free low-firing
- [20] C.F. Tseng, P.A. Lin, Microwave dielectric properties of novel glass-free low-firing Li₂CeO₃ ceramics, J. Am. Ceram. Soc. 97 (2014) 1020–1022.
- [21] J. Liang, W. Lu, W. Lei, G. Fan, H. Ma, A new route to improve microwave dielectric properties of low-temperature sintered Li₂TiO₃-based ceramics, J. Mater. Sci.: Mater. Electron. 24 (2010) 3625–3628.
- [22] Y. Lv, R.Z. Zuo, Y. Cheng, C. Zhang, Low-temperature sinterable (1-x)Ba₃(VO₄)_{2-x} LiMg_{0.9}Zn_{0.1}PO₄ microwave dielectric ceramics, J. Am. Ceram. Soc. 96 (2013) 3862–3867.
- [23] H.F. Zhou, F. He, X. Chen, J. Chen, L. Fang, W. Wang, Y. Miao, A novel thermally stable low-firing LiMg₄V₃O₁₂ ceramic: sintering characteristic, crystal structure and microwave dielectric properties, Ceram. Int. 40 (2014) 6335–6338.
- [24] H.F. Zhou, X.B. Liu, X.L. Chen, L. Fang, Y.L. Wang, ZnLi_{2/3}Ti_{4/3}O₄: a new low loss spinel microwave dielectric ceramic, J. Eur. Ceram. Soc. 32 (2012) 261–265.
- [25] J. Zhang, R.Z. Zuo, A novel self-composite property-tunable LaTiNbO₆ microwave dielectric ceramic, Mater. Res. Bull. 83 (2016) 568–572.
- [26] C. Zhang, R.Z. Zuo, Temperature-stable and high Q composite ceramics in lowtemperature sinterable BaO-V₂O₅ binary system, J. Alloys. Compd. 709 (2017) 234–239.
- [27] M.Z. Dong, Z.X. Yue, H. Zhuang, S.Q. Meng, L.T. Li, Microstructure and microwave dielectric properties of TiO₂-doped Zn₂SiO₄ ceramics synthesized through the sol–gel process, J. Am. Ceram. Soc. 91 (2008) 3981–3985.
- [28] L.X. Pang, D. Zhou, J. Guo, Z.X. Yue, X. Yao, Microwave dielectric properties of (Li_{0.5}Ln_{0.5}) MoO₄ (Ln = Nd, Er Gd, Y, Yb, Sm, and Ce) Ceramics, J. Am. Ceram. Soc. 98 (2015) 130–135.
- [29] H. Xiang, Y. Tang, L. Fang, H. Porwal, C. Li, A novel ultra-low temperature co-fired Na₂BiZn₂V₃O₁₂ ceramic and its chemical compatibility with metal electrodes, J. Mater. Sci.: Mater. Electron. 28 (2017) 1–6.
- [30] E.S. Kim, B.S. Chun, R. Freer, R.J. Cernik, Effects of packing fraction and bond valence on microwave dielectric properties of A²⁺B⁶⁺O₄ (A²⁺: Ca Pb, Ba; B⁶⁺: Mo, W) ceramics, J. Eur. Ceram. Soc. 30 (2010) 1731–1736.
- [31] H. Xie, H. Xi, F. Li, C. Chen, X. Wang, D. Zhou, Microwave dielectric properties of Pb₂MoO₅ ceramic with ultra-low sintering temperature, J. Eur. Ceram. Soc. 34 (2014) 4089–4093.